

MINFILE Number:	093N 272	Name:	TRS	Status:	Prospect
------------------------	----------	--------------	-----	----------------	----------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
FLOAT			Copper	2.12 %	float samples (TR-90-D35, -D36 and R3) taken down slope of the veins yielded values from 0.15 to 2.12 per cent copper, 6.1 to 59.4 grams per tonne silver and 8.29 to 19.43 grams per tonne gold Assessment Report 22372
		Assay/analysis	Silver	59.4 g/t	
1990	N	Grab	Gold	19.43 g/t	
NORTHEAST			Silver	11.7 g/t	grab samples (TR-90-D5 and -D6) from outcrops of tuff and epidote altered granite with quartz veinlets and trace chalcopyrite and pyrite, located approximately 500 metres north east of the main veined zone Assessment Report 22372
		Assay/analysis	Gold	0.93 g/t	
1990	N	Grab			
OUTCROP			Gold	1.56 g/t	two grab samples (TR-90-D44 and -D45) of quartz veined outcrop Assessment Report 22372
		Assay/analysis	Silver	4.4 g/t	
1990	N	Rock	Copper	0.30 %	
TRENCH			Gold	3.66 g/t	over 1.0 metre in trench TR-90-T5 Assessment Report 22372
		Assay/analysis	Silver	24.0 g/t	
1990	N	Chip	Copper	0.54 %	
			Lead	1.44 %	
VEIN			Gold	1.250 g/t	a 3-centimetre channel sample (TRS-9) from a chalcopyrite-bearing quartz vein in a granite porphyry Assessment Report 16759
		Assay/analysis	Silver	3.3 g/t	
1987	N	Channel	Copper	0.146 %	
DRILLHOLE			Gold	1.06 g/t	over 1.52 metres (2.74 to 4.26 metres down-hole), including 0.490 per cent copper over 0.62 metre from a oxidized andesitic volcanic with thin quartz-calcite veinlets in hole TRS 87-1 Assessment Report 16759
		Assay/analysis	Copper	0.490 %	
1987	N	Drill Core			
DRILLHOLE			Lead	1.62 %	over 1.0 metre (from 65.55 to 66.55 metres down-hole) from a silicified to quartz brecciated andesitic volcanic hosting disseminated pyrite in hole TRS 87-4 Assessment Report 16759
		Assay/analysis	Zinc	2.99 %	
1987	N	Drill Core	Silver	254.4 g/t	
SAMPLE			Gold	0.350 g/t	three chip samples (TRS-103R, -118R and -124R) of the intrusive host yielded 0.102, 0.350 and 0.200 gram per tonne gold over 1.0, 1.0 and 2.5 metres, respectively, while a grab sample (TRS-5R) of the intrusive yielded 0.960 gram per tonne gold Assessment Report 15319
		Assay/analysis			
1986	N	Chip			