

MINFILE Number:	093N 272	Name:	TRS	Status:	Prospect
------------------------	----------	--------------	-----	----------------	----------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
FLOAT		Copper	2.12 %	float samples (TR-90-D35, -D36 and R3) taken down slope of the veins yielded values from 0.15 to 2.12 per cent copper, 6.1 to 59.4 grams per tonne silver and 8.29 to 19.43 grams per tonne gold Assessment Report 22372
	Assay/analysis	Silver	59.4 g/t	
1990	Grab	Gold	19.43 g/t	
NORTHEAST		Silver	11.7 g/t	grab samples (TR-90-D5 and -D6) from outcrops of tuff and epidote altered granite with quartz veinlets and trace chalcopyrite and pyrite, located approximately 500 metres north east of the main veined zone Assessment Report 22372
	Assay/analysis	Gold	0.93 g/t	
1990	Grab			
OUTCROP		Gold	1.56 g/t	two grab samples (TR-90-D44 and -D45) of quartz veined outcrop Assessment Report 22372
	Assay/analysis	Silver	4.4 g/t	
1990	Rock	Copper	0.30 %	
TRENCH		Gold	3.66 g/t	over 1.0 metre in trench TR-90-T5 Assessment Report 22372
	Assay/analysis	Silver	24.0 g/t	
1990	Chip	Copper	0.54 %	
		Lead	1.44 %	
VEIN		Gold	1.250 g/t	a 3-centimetre channel sample (TRS-9) from a chalcopyrite-bearing quartz vein in a granite porphyry Assessment Report 16759
	Assay/analysis	Silver	3.3 g/t	
1987	Channel	Copper	0.146 %	
DRILLHOLE		Gold	1.06 g/t	over 1.52 metres (2.74 to 4.26 metres down-hole), including 0.490 per cent copper over 0.62 metre from a oxidized andesitic volcanic with thin quartz-calcite veinlets in hole TRS 87-1 Assessment Report 16759
	Assay/analysis	Copper	0.490 %	
1987	Drill Core			
DRILLHOLE		Lead	1.62 %	over 1.0 metre (from 65.55 to 66.55 metres down-hole) from a silicified to quartz brecciated andesitic volcanic hosting disseminated pyrite in hole TRS 87-4 Assessment Report 16759
	Assay/analysis	Zinc	2.99 %	
1987	Drill Core	Silver	254.4 g/t	
SAMPLE		Gold	0.350 g/t	three chip samples (TRS-103R, -118R and -124R) of the intrusive host yielded 0.102, 0.350 and 0.200 gram per tonne gold over 1.0, 1.0 and 2.5 metres, respectively, while a grab sample (TRS-5R) of the intrusive yielded 0.960 gram per tonne gold Assessment Report 15319
	Assay/analysis			
1986	Chip			