

MINFILE Number:		Name:		Status:	
Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments	
NORTHWEST					
2010 N	Assay/analysis Grab	Gold Silver Copper	0.145 g/t 8.7 g/t 0.015 %	A sample (26065) from a zone of anomalous mineralization is reported on an east-west trending ridge, approximately 3 kilometres to the northwest of the main A zone. Also yielded 0.050 per cent lead and 0.037 per cent zinc. Assessment Report 31960	
A 1991 N	Assay/analysis Drill Core	Gold Copper	0.243 g/t 0.101 %	Diamond drilling yielded intercepts of 0.191 gram per tonne gold over 24 metres in hole 91-8; 0.101 per cent copper over 41.46 metres in hole 91-10 and 0.243 gram per tonne gold over 20 metres, including 2.250 grams per tonne gold over 2 metres in hole 91-12. These drill holes were located from 400 metres north to 800 metres north east and east of the main trenched A zone. Assessment Report 22034	
A 1990 N	Assay/analysis Drill Core	Copper Gold	0.025 % 0.84 g/t	Drilling on the A zone yielded intercepts including 0.016 per cent copper and 0.31 gram per tonne gold over 8 metres (27 to 35 metres down-hole) in hole 90-02; 0.025 per cent copper and 0.84 gram per tonne gold over 14 metres (58 to 72 metres down-hole) in hole 90-03; 0.019, 0.059 and 0.170 per cent copper with 0.34, 0.50 and 0.33 gram per tonne gold over 33.3, 8.76 and 7.44 metres (16.50 to 49.80, 64.00 to 72.76 and 104.0 to 114.44 metres down-hole), respectively, in hole 90-4 and 0.015 per cent copper with 1.18 grams per tonne gold over 5.68 metres (7.32 to 13.0 metres down-hole) in hole 90-5. Assessment report 20612	
A 1990 N	Assay/analysis Trench	Gold Copper	1.00 g/t 0.043 %	Trenching on the A zone yielded 0.92 and 1.00 gram per tonne gold with 0.071 and 0.043 per cent copper over 8 metres each in trenches no. 4 and 2, respectively. Assessment Report 20612	
NORTHEAST					
1989 N	Assay/analysis Grab	Copper	0.127 %	Grab sample (34033) from a zone of anomalous copper mineralization is located on an east-west trending ridge, approximately 2 kilometres to the northeast of the main A zone. Assessment Report 19719	
A 1989 N	Assay/analysis Grab	Gold Silver Copper Molybdenum	5.21 g/t 17.8 g/t 0.260 % 0.027 %	Five grab samples (34965 through 34969) from the A zone yielded from 0.651 to 3.409 grams per tonne gold, 3.2 to 17.8 grams per tonne silver, 0.058 to 0.260 per cent copper and 0.001 to 0.027 per cent molybdenum, while another grab sample (34525), taken approximately 100 metres to the west-southwest of the previous samples, yielded 5.210 grams per tonne gold. Assessment Report 19719	

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
-----------------------------	----------------------	-----------	-------	------------------------