

MINFILE Number: 094D 078	Name: ROY	Status: Showing
---------------------------------	------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
TRENCH 2004 N	Assay/analysis Grab	Gold Silver	9.51 g/t 46.1 g/t	two grab samples (527670 and 527671) from trench 5 McCrea, J.A. (2011-03-07): Technical Report on the Day Property
STOCKWORK 1990 N	Assay/analysis Chip	Gold Copper	0.5480 g/t 0.1210 %	The weighted average over a 62-metre interval. Assessment Report 21359.
SHEAR 1985 N	Assay/analysis Chip	Copper Gold Silver	1.20 % 8.7 g/t 16.8 g/t	samples (SU2250 to SU2253) of a silicified shear within the porphyry yielded from 0.40 to 1.20 per cent copper, 2.0 to 16.8 grams per tonne silver and 1.8 to 8.7 grams per tonne gold over 1.0 metre McCrea, J.A. (2011-03-07): Technical Report on the Day Property