

<b>MINFILE Number:</b>	094D 158	<b>Name:</b>	HAT	<b>Status:</b>	Prospect
------------------------	----------	--------------	-----	----------------	----------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
2005	N	Assay/analysis	Copper	0.53 %	Significant results from the 2005 drill program included 9 metres averaging 0.53 per cent copper and 266 parts per billion gold in drill hole R05-04. Assessment Report 28496.
		Drill Core	Gold	0.266 g/t	
2005	N	Assay/analysis	Copper	0.16 %	Drill hole R05-04 averaged 0.16 per cent copper over 47.9 metres. Assessment Report 28496.
		Drill Core			
2004	N	Assay/analysis	Copper	0.26 %	The best result obtained from the Gitennes Exploration 2004 drill program was a 36.5-metre section grading 0.26 per cent copper and 122 parts per billion gold. Assessment Report 27622.
		Drill Core	Gold	0.122 g/t	
1984	N	Assay/analysis	Gold	0.4000 g/t	A 3-metre drill interval from drill hole R-84-11. Assessment Report 13316.
		Drill Core	Copper	0.9300 %	