

MINFILE Number:	094E 002	Name:	FIRESTEEL	Status:	Developed Prospect
------------------------	----------	--------------	-----------	----------------	--------------------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
MAIN			Zinc	10.5 %	Chip sample 96T107 over 1 metre, while four samples (11603 to 11606) from the main zone yielded from 12 to 44 per cent zinc, 0.25 to 0.74 per cent copper and 2.7 to 195 grams per tonne silver. Assessment Report 25003.
1996	N	Assay/analysis Chip			
SAMPLE			Silver	11163 g/t	Samples of the freibergite-bearing quartz veins over 0.46 metre, and 1134 grams per tonne silver over 1.2 metres. Assessment Report 13531.
1980	N	Assay/analysis Rock			
MAIN		27,216 t Unclassified	Silver Copper Zinc	34.2900 g/t 0.3000 % 10.0000 %	Source of quantity of ore reserves is unknown. Assessment Reports 4200 (reserves); 14118 (grades).
1973	Y				
SOUTHEAST			Zinc Lead Silver	2.3 % 0.3 % 106.0 g/t	Sampling of the southeastern zone exposed in trench no. 57 over 2.1 metres. Assessment Report 25003.
1947	N	Assay/analysis Chip			
SOUTHWEST			Zinc Copper Silver	0.80 % 1.2 % 177.8 g/t	Sampling of the southwestern zone exposed in trench no. 101 over 0.9 metre. Assessment Report 25003.
1947	N	Assay/analysis Chip			
MAIN			Zinc Copper Silver	11.5 % 0.50 % 54.0 g/t	Sample 14152 over 4.8 metres. Assessment Report 25003.
1933	N	Assay/analysis Chip			