

<b>MINFILE Number:</b> 094E 022	<b>Name:</b> ATTYCELLEY	<b>Status:</b> Prospect
---------------------------------	-------------------------	-------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
VEIN		Gold	0.15 g/t	Rock sample WG15-13. Assessment Report 35865.
	Assay/analysis	Silver	73 g/t	
2015	Rock	Copper	0.58 %	
		Lead	1 %	
		Zinc	1 %	
WEST		Silver	268.0 g/t	A 0.5-metre-long sample (Att-90-008) of host volcanics with jarosite. Assessment Report 21059.
	Assay/analysis	Gold	0.22 g/t	
1990	Grab	Lead	14.6 %	
		Zinc	2.55 %	
		Copper	0.433 %	
EAST		Gold	0.45 g/t	Sampling over 1.0 metre of shattered and oxidized quartz vein material from the east zone (sample Att-90-22). Assessment Report 21059.
	Assay/analysis	Silver	201.0 g/t	
1990	Grab	Copper	0.94 %	
		Lead	0.46 %	
		Zinc	0.27 %	
VEIN		Silver	30.7000 g/t	Sample Att-90-011 over 1.0 metre from the west vein zone; one of 13 samples taken from the west zone of the showing. Assessment Report 21059.
	Assay/analysis	Gold	0.0100 g/t	
1990	Grab	Copper	0.4070 %	
		Lead	2.5000 %	
		Zinc	3.4000 %	
VEIN		Lead	2.65 %	A grab sample (53885) of select vein material. Assessment Report 10113.
	Assay/analysis	Silver	101.5 g/t	
1981	Grab	Zinc	0.69 %	
		Copper	0.34 %	
		Gold	0.035 g/t	
VEIN		Copper	0.47 %	Three rock samples (91929, 91926 and 91928) of mineralized quartz vein material yielded values from 0.20 to 0.47 per cent copper, 0.61 to 4.20 per cent lead, 0.51 to 3.10 per cent zinc, 20.9 to 63.3 grams per tonne silver, and 0.07 to 2.05 grams per tonne gold. Assessment Report 6650.
	Assay/analysis	Lead	4.20 %	
1977	Rock	Zinc	3.10 %	
		Silver	63.3 g/t	
		Gold	2.05 g/t	
GOSSAN		Copper	0.34 %	A sample of gossanous material to the west. Assessment Report 6650.
	Assay/analysis	Lead	12.10 %	
1977	Rock	Zinc	6.30 %	
		Silver	171.3 g/t	
		Gold	0.4 g/t	