

<b>MINFILE Number:</b> 094E 027	<b>Name:</b> CASTLE MOUNTAIN	<b>Status:</b> Showing
---------------------------------	------------------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SKARN 1989	N Assay/analysis Grab	Silver Copper Lead Zinc	70.6 g/t 1.802 % 5.198 % 18.410 %	three samples (PD-84 to -86) from the main Castle massive galena-sphalerite skarn zone yielded values from 33.4 to 70.6 grams per tone silver, 0.253 to 1.802 per cent copper, 4.112 to 5.198 per cent lead and 6.408 to 18.410 per cent zinc  Property File - Delancy, P.R. [1989-10-01]: Final report on the 1989 exploration program Chappelle Property
SOUTH 1989	N Assay/analysis Grab	Gold Silver Lead Zinc	0.007 g/t 5.1 g/t 0.298 % 1.497 %	sample PD-106 of mineralized skarn, taken approximately 600 metres to the south of the main zone  Property File - Delancy, P.R. [1989-10-01]: Final report on the 1989 exploration program Chappelle Property
WEST 1989	N Assay/analysis Grab	Gold Silver Lead Zinc	0.443 g/t 37.2 g/t 0.419 % 4.198 %	sample PD-98 of mineralized skarn, taken approximately 400 metres west of the main zone  Property File - Delancy, P.R. [1989-10-01]: Final report on the 1989 exploration program Chappelle Property
SKARN 1973	N Assay/analysis Chip	Silver Copper Zinc	10.6 g/t 0.20 % 4.0 %	a sample taken across 4.5 metres from the southern end of the main skarn zone  Property File – Crowhurst, J.J. [1973-06-25]: Report of the Castle Mountain Property of Oswood G. MacDonald to Macsan Explorations Ltd.
SKARN 1967	N Assay/analysis Grab	Lead Zinc Silver	1.05 % 12.0 % 390 g/t	a sample (44706) of mineralized limestone (skarn?)  Property File - Cordilleran Exploration Corp. Ltd [1968-02-01]: Report - 1967-69 Toodoggone
SKARN 1931	N Assay/analysis Chip	Silver Copper Lead Zinc	47.9900 g/t 0.7900 % 3.9000 % 32.5000 %	Assessment Report 14979.