

MINFILE Number:		094E 027	Name:		CASTLE MOUNTAIN	Status:	Showing
Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments		
SKARN			Silver	70.6 g/t	three samples (PD-84 to -86) from the main Castle massive galena-sphalerite skarn zone yielded values from 33.4 to 70.6 grams per tone silver, 0.253 to 1.802 per cent copper, 4.112 to 5.198 per cent lead and 6.408 to 18.410 per cent zinc		
1989	N	Assay/analysis Grab	Copper	1.802 %	Property File - Delancy, P.R. [1989-10-01]: Final report on the 1989 exploration program Chappelle Property		
SOUTH			Lead	5.198 %	sample PD-106 of mineralized skarn, taken approximately 600 metres to the south of the main zone		
1989	N	Assay/analysis Grab	Zinc	18.410 %	Property File - Delancy, P.R. [1989-10-01]: Final report on the 1989 exploration program Chappelle Property		
WEST			Gold	0.007 g/t	sample PD-98 of mineralized skarn, taken approximately 400 metres west of the main zone		
1989	N	Assay/analysis Grab	Silver	37.2 g/t	Property File - Delancy, P.R. [1989-10-01]: Final report on the 1989 exploration program Chappelle Property		
SKARN			Lead	0.419 %	sample PD-98 of mineralized skarn, taken approximately 400 metres west of the main zone		
1973	N	Assay/analysis Chip	Zinc	4.198 %	Property File - Delancy, P.R. [1989-10-01]: Final report on the 1989 exploration program Chappelle Property		
SKARN			Silver	10.6 g/t	a sample taken across 4.5 metres from the southern end of the main skarn zone		
1967	N	Assay/analysis Grab	Copper	0.20 %	Property File - Cordilleran Exploration Corp. Ltd [1968-02-01]: Report - 1967-69 Toodoggone		
SKARN			Zinc	4.0 %	a sample (44706) of mineralized limestone (skarn?)		
1931	N	Assay/analysis Chip	Silver	390 g/t	Property File - Cordilleran Exploration Corp. Ltd [1968-02-01]: Report - 1967-69 Toodoggone		
			Copper	0.7900 %	Assessment Report 14979.		
			Lead	3.9000 %			
			Zinc	32.5000 %			