

MINFILE Number:	094E 036	Name:	EHL	Status:	Showing
------------------------	----------	--------------	-----	----------------	---------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
FLOAT			Copper	1.44 %	four float samples (M456707-708 and M456719- 720) of mineralized quartz veining from the area averaged 1.44 per cent copper, 1.3 grams per tonne gold and 45 grams per tonne silver Assessment Report 36482
2016	N	Assay/analysis Grab	Gold	1.3 g/t	
			Silver	45 g/t	
SAMPLE			Tungsten	0.042 %	a sample from 0.4 metre wide banded quartz-pyrite vein yielded 0.042 per cent tungsten with low base and precious metals Assessment Report 36482
2016	N	Assay/analysis Chip			
FLOAT			Gold	21.75 g/t	samples of mineralized quartz vein float (185332, 185338, 185404) from the area assayed 10.53, 11.25 and 21.75 grams per tonne gold, 22.2, 28.4 and 38.2 grams per tonne silver with 1.00, 0.03 and 0.321 per cent copper, respectively Assessment Report 27638
2004	N	Assay/analysis Grab	Silver	38.2 g/t	
			Copper	1 %	
SAMPLE			Copper	0.413 %	chip samples (CR-2, FR-10 through -12) from a silicified zone in volcanic porphyry hosting disseminated pyrite and chalcopyrite yielded from 0.134 per cent copper over 2.00 metres to 0.413 per cent copper over 0.30 metre, while a sample (KR-7) of malachite-stained silicified andesite assayed 0.217 per cent copper Assessment Report 18763
1989	N	Assay/analysis Chip			
SAMPLE			Silver	13.0000 g/t	Sample AT-86-R-04, one of two anomalous grab samples taken in 1986. Sampling in 1989 yielded higher copper values. Assessment Report 15818.
1986	N	Assay/analysis Grab	Gold	1.7000 g/t	
			Copper	0.4915 %	