

MINFILE Number:	094E 052	Name:	GORD 9	Status:	Showing
------------------------	----------	--------------	--------	----------------	---------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
2005	N	Assay/analysis Chip	Gold	2.38 g/t	three chip samples (64339 through 64341) over 0.2 to 0.4 metres from a 0.2 metre wide quartz vein hosting chalcopyrite and pyrite, exposed over 10 metres along a strike of 042 to 046 degrees and dipping 78 to 80 degrees, yielded from 0.37 to 2.38 grams per tonne gold, 7.1 to 21.5 grams per tonne silver and 3.84 to 7.74 per cent copper Assessment Report 28039
			Silver	21.5 g/t	
			Copper	7.74 %	
2004	N	Assay/analysis Grab	Gold	5.745 g/t	Sample 148905 Assessment Report 27638
			Silver	200 g/t	
1974	N	Assay/analysis Chip	Silver	30.0000 g/t	A 91-centimetre chip sample. Assessment Report 5194.
			Copper	0.1075 %	
			Lead	0.4300 %	
			Zinc	1.9000 %	