

MINFILE Number:	094E 070	Name:	MESS	Status:	Prospect
------------------------	----------	--------------	------	----------------	----------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SOUTHWEST		Lead	0.588 %	Six samples (G06241 to G06247) from the same area as the 2004 samples yielded from 0.058 to 0.588 per cent lead, 0.004 to 0.139 per cent zinc, 10.4 to 75.1 grams per tonne silver and 0.07 to 0.18 gram per tonne gold. Assessment Report 28649.
	Assay/analysis	Zinc	0.139 %	
2006	Rock	Silver	75.1 g/t	
		Gold	0.18 g/t	
SOUTHWEST		Silver	5600 g/t	A sample of vein material taken 300 metres to the southwest. Assessment Report 27636.
	Assay/analysis			
2004	Rock			
TRENCH		Gold	7.33 g/t	Grab sampling of the North trench area over 1.5 metres. Assessment Report 27429.
	Assay/analysis	Silver	5400.0 g/t	
2003	Grab	Copper	0.23 %	
		Zinc	1.67 %	
		Lead	14.25 %	
TRENCH		Gold	0.59 g/t	Average of channel samples over 1.8 metres. Assessment Report 27429.
	Assay/analysis	Silver	419.4 g/t	
2003	Channel	Copper	0.04 %	
		Lead	1.73 %	
		Zinc	0.09 %	
A		Gold	0.29 g/t	Samples from the A zone. Assessment Report 19789.
	Assay/analysis	Silver	61 g/t	
1989	Grab			
TRENCHES		Silver	856.3000 g/t	Grades are from one of four samples from trench 1 taken in 1986. Assessment Report 15184.
	Assay/analysis	Gold	0.4250 g/t	
1986	Grab	Copper	0.3731 %	
		Lead	5.2669 %	
		Zinc	1.7435 %	
TRENCH		Silver	501.94 g/t	Chip sampling over 6 metres of the wall of trench 1. Assessment Report 10235.
	Assay/analysis	Gold	0.24 g/t	
1981	Chip			
TRENCH		Gold	1.5 g/t	A 1.0 metre chip sample from trench 2. Assessment Report 10235.
	Assay/analysis			
1981	Chip			
FLOAT		Gold	0.79 g/t	Quartz vein float sample JC-14-80-21. Assessment Report 8999.
	Assay/analysis	Silver	44.8 g/t	
1980	Grab			