

MINFILE Number:	094E 072	Name:	PAU	Status:	Prospect
------------------------	----------	--------------	-----	----------------	----------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
MAIN			Gold	0.40 g/t	Seven samples of quartz vein material from the Perry Mason (Black Pete) zone yielded values from 0.10 to 0.40 gram per tonne gold with 1.4 to 77.1 grams per tonne silver. Assessment Report 34394
2012	N	Assay/analysis Rock	Silver	77.1 g/t	
MAIN			Gold	1.54 g/t	Samples from former trenches yielded up to 1.54 grams per tonne gold and 159.8 grams per tonne silver (Sample PM#3). Assessment Report 25226
1997	N	Assay/analysis Grab	Silver	159.8 g/t	
MAIN			Silver	100.4600 g/t	Grades are the weighted average of 11 samples over a 21.66 metres interval from drillhole 87PM6. Assessment Report 16476.
1987	N	Assay/analysis Drill Core	Gold	0.3100 g/t	
MAIN			Gold	164.9 g/t	A mineralized area exposed over approximately 65 metres in trenches 85-8, -5 and -6 on the Black Pete zone which yielded values of up to 121.4 grams per tonne gold with 7335.9 grams per tonne silver over 1 metre in trench 85-8 and 164.9 grams per tonne gold with 2694.9 grams per tonne silver over 3 metres. Assessment Report 14645 and 16476
1985	N	Assay/analysis Chip	Silver	2694.9 g/t	
MAIN			Gold	0.29 g/t	Sampling of the trenches averaged 0.29 gram per tonne gold and 39.7 grams per tonne silver from 53 samples with values of up to 3.8 grams per tonne gold and 297.5 grams per tonne silver. Assessment Report 11540
1983	N	Assay/analysis Rock	Silver	39.7 g/t	
MAIN			Gold	0.9 g/t	Sampling of the Black Pete zone yielded values of up to 2.7 grams per tonne gold with 490.3 grams per tonne silver over 1.0 metre and averaged 0.9 gram per tonne gold with 164.2 grams per tonne silver over 12 metres from trench P.M. 1. Assessment Report 10788
1982	N	Assay/analysis Chip	Silver	164.2 g/t	
SKARN			Gold	3.4 g/t	A sample (PM22-82) from the galena-bearing skarn zone. Assessment Report 10788
1982	N	Assay/analysis Rock	Silver	17.1 g/t	
SOUTHWEST			Silver	576.0 g/t	A sample (PM-4-82) from a quartz-galena vein, located approximately 900 metres to the southwest. Assessment Report 10788
1982	N	Assay/analysis Rock			
WEST			Silver	30.8 g/t	A sample from a silicified granite, located approximately 1.3 kilometres to the west-southwest. Assessment Report 9973
1981	N	Assay/analysis Rock			

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
SKARN			Gold	0.59 g/t	A rock sample from a siliceous skarn zone along an intrusive contact.
1981	N	Assay/analysis Rock			Assessment Report 9973
SKARN			Gold	0.155 g/t	A rock sample (SC-34-79-21) of skarn hosting
		Assay/analysis	Silver	86.0 g/t	galena-sphalerite mineralization, located to the
1980	N	Rock	Zinc	0.245 %	south-southwest.
			Lead	4.90 %	Assessment Report 8434