

<b>MINFILE Number:</b>	094E 082	<b>Name:</b>	WRICH 2	<b>Status:</b>	Prospect
------------------------	----------	--------------	---------	----------------	----------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
2023	Y	Assay/analysis	Copper	0.03 %	DDH JP22044: 108 metre intercept, from 59 to 167 metre downhole; includes 21 metres of 0.04 per cent copper, 0.32 gram per tonne gold and 13.6 grams per tonne silver Assessment Report 40912
		Drill Core	Gold	0.23 g/t	
			Silver	6.4 g/t	
2003	N	Assay/analysis	Gold	2.46 g/t	Samples taken from an area located approximately 500 metres to the north-northeast. Assessment Report 27429.
		Rock	Silver	409.6 g/t	
2003	N	Assay/analysis	Gold	0.10 g/t	Over 18.0 metres in drillhole W03-03. Assessment Report 27429.
		Drill Core	Silver	9.9 g/t	
2003	N	Assay/analysis	Silver	15 g/t	Assay of 10 to 20 grams per tonne silver over 83 metres in drillhole W03-04. Assessment Report 27429.
		Drill Core			
2003	N	Assay/analysis	Gold	0.11 g/t	Over 98.2 and 0.29 grams per tonne gold across 39.1 metres in drillhole W03-06. Assessment Report 27429.
		Drill Core	Silver	8.1 g/t	
2003	N	Assay/analysis	Gold	0.12 g/t	Over 82.8 metres in drillhole W03-07. Assessment Report 27429.
		Drill Core	Silver	13.4 g/t	
2003	N	Assay/analysis	Gold	0.26 g/t	Results from a 67 metre drill interval. Assessment Report 27429.
		Chip	Silver	11.3 g/t	
2003	N	Assay/analysis	Gold	81.1 g/t	Assessment Report 27429.
		Chip	Silver	405 g/t	
2002	N	Assay/analysis	Gold	0.81 g/t	Chip sampling of trenches 1, 2 and 3 over an average 105 metres and selected sections include: 20.0 metres assaying 2.86 grams per tonne gold, 7.0 grams per tonne silver, including 12.0 metres yielding 2.65 grams per tonne gold, 18.0 grams per tonne silver in trench 2. Assessment Report 27160.
		Chip	Silver	9.2 g/t	

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
SOUTH	2000	N	Assay/analysis Grab	Gold	A sample of subcrop, taken approximately 200 metres to the south, of hematite-stained crystal lithic tuff hosting a 5-centimetre-wide chalcedonic quartz-clay vein. Assessment Report 26545.
				Silver	
SAMPLE	2000	N	Assay/analysis Rock	Gold	Assessment Report 26545.
				Silver	
DRILLHOLE	1987	N	Assay/analysis Drill Core	Gold	Over a 1-metre interval from 81 to 82 metres down hole in drillhole 87-W3. Assessment Report 16470.
				Silver	
DRILLHOLE	1987	N	Assay/analysis Drill Core	Gold	Over a 1-metre interval 224 to 225 metres down hole in drillhole 87-W2. Assessment Report 16470.
				Silver	
SAMPLE	1985	N	Assay/analysis Rock	Gold	Four rock samples (WR-851 to WR-854) yielded from trace to 1.37 grams per tonne gold and 3.4 to 20.5 grams per tonne silver. Assessment Report 14069.
				Silver	
SAMPLE	1982	N	Assay/analysis Grab	Gold	A sample (EDW-1) of hematized and clay-altered tuff. Assessment Report 10705.
				Silver	
SAMPLE	1982	N	Assay/analysis Grab	Gold	A float or sub-crop sample (EDW-43) of oxidized quartz vein material, located near outcrop to the south. Assessment Report 10705.
				Silver	
SAMPLE	1981	N	Assay/analysis Grab	Silver	Best grab sample (SC-48-81-12) of chalcedony, clay and iron oxides from the alteration zone. Assessment Report 10705.
				Gold	