

|                                 |                          |                         |
|---------------------------------|--------------------------|-------------------------|
| <b>MINFILE Number:</b> 094E 096 | <b>Name:</b> BELLE SOUTH | <b>Status:</b> Prospect |
|---------------------------------|--------------------------|-------------------------|

| Ore Zone/<br>Year/Report On | Tonnage/<br>Category | Commodity | Grade       | Reference/<br>Comments  |
|-----------------------------|----------------------|-----------|-------------|---|
| TRENCH                      |                      | Gold      | 0.778 g/t   | a sample (1710239) of oxidized silica in epidote-chlorite-pyrite altered andesite from a former trench yielded 0.778 grams per tonne gold, greater than 100 grams per tonne silver and 0.224 per cent lead<br>Assessment Report 33556 |
| 2012                        | Assay/analysis       | Silver    | 100 g/t     |   |
| N                           | Rock                 | Lead      | 0.224 %     |   |
| SAMPLE                      |                      | Silver    | 42.8000 g/t | Sample 22185, a 1-metre chip sample from Trench T-B-88-10.<br>Assessment Report 18627.  |
| 1988                        | Assay/analysis       | Gold      | 6.8200 g/t  |   |
|                             | Chip                 |           |             |   |