

<b>MINFILE Number:</b>	094E 137	<b>Name:</b>	PUL 1	<b>Status:</b>	Prospect
------------------------	----------	--------------	-------	----------------	----------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE  2006	N	Assay/analysis Rock	Copper	0.332 %	A rock sample (C198133) from an outcrop of altered limestone. Assessment Report 28700
			Gold	2.16 g/t	
SOUTH  1997	N	Assay/analysis Grab	Gold	15.62 g/t	Nine samples (S97-4A, 4B, 14, 15, 16, 17, 18, 19, 20) of mineralized skarn were collected approximately 500 metres to the south and yielded from 0.02 to 15.62 grams per tonne gold, 18.9 to 192.0 grams per tonne silver with up to 4.410 per cent copper, 1.49 per cent lead and 10.80 per cent zinc. Assessment Report 25220
			Silver	192.0 g/t	
			Copper	4.410 %	
			Lead	1.49 %	
			Zinc	10.80 %	
WEST  1997	N	Assay/analysis Grab	Gold	7.86 g/t	Sample L100+80N,100+25E, taken approximately 450 metres to the west. Assessment Report 25220
			Silver	275.0 g/t	
			Copper	4.570 %	
SAMPLE  1997	N	Assay/analysis Grab	Gold	3.33 g/t	Grab sample L98+10N,104+20E. Assessment Report 25220
			Silver	41.8 g/t	
			Copper	1.760 %	
SAMPLE  1983	N	Assay/analysis Grab	Silver	144.0000 g/t	Sample MB 1-82, one of two samples taken from the eastern end of the skarn zone. Gold value is less than 0.343 gram per tonne. Assessment Report 11106.
			Gold	0.3430 g/t	