

<b>MINFILE Number:</b> 094E 170	<b>Name:</b> WOOF	<b>Status:</b> Showing
---------------------------------	-------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE 2018	N Assay/analysis Grab	Gold Silver	3.45 g/t 9.5 g/t	a select grab sample (100364) of epithermal quartz veinlets in weakly silica-chlorite altered andesite(?) Assessment Report 38203
SAMPLE 2015	N Assay/analysis Grab	Gold Silver	35.4 g/t 44.8 g/t	samples from the Woof zone Assessment Report 33556
SAMPLE 1995	N Assay/analysis Chip	Gold Silver	18.5 g/t 334.0 g/t	three chip samples (957, 976 and 987) from the Woof zone yielded 18.0, 18.5 and 8.2 grams per tonne gold with 28.8, 26.2 and 334.0 grams per tonne silver over 1.0 metre each, respectively, while a grab sample (958) mineralized calcite veining assayed 63.3 grams per tonne gold, 34.3 grams per tonne silver, 0.154 per cent copper, 0.400 per cent lead and 1.43 per cent zinc Assessment Report 24284
SAMPLE 1994	N Assay/analysis Grab	Gold Silver	96.36 g/t 69.4 g/t	two grab samples (145615 and 145616) from the Woof zone Assessment Report 23663
NORTH 1988	N Assay/analysis Grab	Gold Silver	5.3 g/t 3650 g/t	Assessment Report 18015
SOUTH 1988	N Assay/analysis Grab	Gold Silver	34.0 g/t 23.09 g/t	Assessment Report 18015.
NORTH 1983	N Assay/analysis Grab	Gold Silver	79.2 g/t 30.5 g/t	Grab sample 26070 Assessment Report 11843
SAMPLE 1981	N Assay/analysis Rock	Gold Silver	32.57 g/t 30.86 g/t	two samples (1543 and 18456) of siliceous hematitic breccia near the contact of green and maroon volcanics were collected from the area of the Woof occurrence Assessment Report 9372