

MINFILE Number: 094E 174	Name: JOANNA EAST	Status: Showing
---------------------------------	--------------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE 2005	N Assay/analysis Chip	Gold Silver Copper	13.00 g/t 13.6 g/t 0.129 %	a 0.9 metre chip sample (64641) from a quartz vein with pyrite, trending 320 to 340 degrees and traced for over 400 metres along strike, yielded 13.00 grams per tonne gold, 13.6 grams per tonne silver and 0.129 per cent copper, while three other chip samples (64639, 64640 and 64642) yielded from 1.36 to 12.10 grams per tonne gold, 5.1 to 27.6 grams per tonne silver and 0.236 to 0.687 per cent copper Assessment Report 28039
SAMPLE 2004	N Assay/analysis Chip	Gold Silver Copper	22.61 g/t 16.6 g/t 0.723 %	a 0.1 metre chip sample (148902) from a brecciated quartz vein with chalcopyrite and malachite Assessment Report 27638
SAMPLE 1990	N Assay/analysis Grab	Silver Gold Copper	7.2000 g/t 3.7700 g/t 1.6400 %	Sample JD-047, a grab sample of frost heave vein material. Assessment Report 20671.
NORTHEAST 1988	N Assay/analysis Chip	Gold Silver Lead Copper	0.485 g/t 19.5 g/t 0.887 % 1.398 %	a grab and chip samples (DO-106, DO-121 through -130) of and quartz veined andesitic volcanic with pyrite and chalcopyrite, located approximately 200 to 350 metres to the north east Assessment Report 20671
SAMPLE 1988	N Assay/analysis Chip	Gold Silver Copper	7.80 g/t 90.0 g/t 1.130 %	two chip samples (33218 and 33222) of quartz veining with malachite, pyrite and chalcopyrite hosted by volcanic tuff and breccia near its contact with an andesitic porphyry yielded 7.80 and 3.50 grams per tonne gold, 7.6 and 90.0 grams per tonne silver with 0.378 and 1.130 per cent copper over 0.15 metre each, respectively Assessment Report 18536
SOUTHWEST 1988	N Assay/analysis Chip	Gold Silver Copper	0.465 g/t 5.2 g/t 0.195 %	a chip sample (JD-010) from a silicified shear zone in a propylitic altered andesite with chalcopyrite and pyrite, located approximately 150 metres to the south west Assessment Report 20671
SAMPLE 1986	N Assay/analysis Grab	Gold Silver Copper	9.50 g/t 6.9 g/t 0.581 %	, a grab sample (JS-86-006) of quartz with malachite Assessment Report 15338