

| | | |
|---------------------------------|-----------------|------------------------|
| MINFILE Number: 094E 201 | Name: WG | Status: Showing |
|---------------------------------|-----------------|------------------------|

| Ore Zone/ Year/Report On | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
|-----------------------------|------------------------------|------------|-----------|--|
| VEIN | | Molybdenum | 0.02 % | 2022 Rock Sample D992356: coxcomb textured quartz vein with galena and sphalerite Assessment Report 40755 |
| | Assay/analysis | Lead | 3.45 % | |
| 2023 | Grab | Zinc | 12.55 % | |
| DRILLHOLE | | Silver | 31.0 g/t | Diamond drilling on the WG Upper (south east) zone yielded intercepts including 18.3 grams per tonne silver over 3.0 metres in hole PN04-17 and 31.0 grams per tonne silver over 1.60 metres in hole PN04-18 Assessment Report 27602 |
| 2004 | Assay/analysis Drill Core | | | |
| DRILLHOLE | | Gold | 0.266 g/t | Drilling on the WG Lower (north west) zone yielded intercepts of 0.56 per cent molybdenum over 0.7 metre in hole PN04-19, 0.266 gram per tonne gold, 4.1 grams per tonne silver and 1.40 per cent combined lead-zinc over 0.9 metres in hole PN04-20 Assessment Report 27602 |
| | Assay/analysis | Silver | 4.1 g/t | |
| 2004 | Drill Core | | | |
| SAMPLE | | Gold | 16.8 g/t | Assessment Report 27602. |
| 2004 | Assay/analysis Grab | | | |
| FLOAT | | Gold | 16.82 g/t | Float samples collected over a length of over 300 metre of the northwest portion of the NW zone range from 0.5 to 7.06 grams per tonne gold, 1.2 to 6.4 grams per tonne silver and up to 0.019 per cent molybdenum, while a sample (WG-PN-03-033-07) of quartz float containing native gold and possible electrum, taken from the south east end of the WG zone, yielded 16.82 grams per tonne gold and 29.8 grams per tonne silver Assessment Report 27310 |
| | Assay/analysis | Silver | 29.8 g/t | |
| 2003 | Rock | | | |
| TRENCHES | | Gold | 0.61 g/t | Sampling of trench WG040 yielded 0.846 per cent lead, 0.469 per cent zinc over 4.2 metres, including 0.118 gram per tonne gold, 8.2 grams per tonne silver, 1.76 per cent lead and 0.98 per cent zinc over 1.4 metres, while trench WG041 yielded values of 0.61 gram per tonne gold, 21.2 grams per tonne silver, 2.75 per cent lead and 2.14 per cent zinc over 1.10 metre and 0.122 gram per tonne gold, 103 grams per tonne silver and 0.642 per cent lead over 0.90 metres. The trenches are in the north west end of the WG zone. Assessment Report 27055 |
| | Assay/analysis | Silver | 21.2 g/t | |
| | Chip | Lead | 2.75 % | |
| | | Zinc | 2.14 % | |
| 2002 | | N | | |
| FLOAT | | Gold | 4.93 g/t | Sampling of phyllic altered intrusive with quartz stockworks, exposed in sub-crop and float by hand trenching in the south east end of the WG zone Assessment Report 27055 |
| 2002 | Assay/analysis Rock | | | |

| Ore Zone/ Year/Report On | | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
|-----------------------------|---|---------------------------|----------------|-------------------------|--|
| SAMPLE 1998 | N | Assay/analysis Rock | Gold Silver | 0.292 g/t 2.2 g/t | An oxidized rock sample (PJB-17) containing pyrite, taken from the north side of the ridge Assessment Report 25811 |
| TRENCH 1985 | N | Assay/analysis Channel | Silver Gold | 2.1000 g/t 0.175 g/t | Channel sampling of trenches in the vicinity of the reported galena mineralization, located in the south east end of the WG zone, yielded up to 2.1 grams per tonne silver over 2.0 metres in trench 5 and 0.175 gram per tonne gold over 2.0 metres in trench 3, while nearby rock samples yielded up to 0.209 gram per tonne gold and 3.4 grams per tonne silver Assessment Report 15264. |
| SAMPLE 1980 | N | Assay/analysis Rock | Gold Silver | 0.31 g/t 3.8 g/t | Rock sample (SC-28-80-16) of banded quartz in a volcanic host, taken approximately 400 metres south of the later Trench 5 and on the south side of the ridge, yielded 0.31 gram per tonne gold and 3.8 grams per tonne silver, while a rock sample (SC-29-80-4) of volcanic with malachite fracture filings, taken a short distance further south east, yielded 0.07 gram per tonne gold, 2.1 grams per tonne silver and 0.901 per cent copper Assessment Report 9001 |