

MINFILE Number: 094E 244	Name: AUGUST	Status: Showing
---------------------------------	---------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
NORTHEAST		Copper	0.611 %	Sample 2691918 from the northeast zone.
2014	Assay/analysis Rock	Lead	0.423 %	Assessment Report 34942.
		Zinc	0.264 %	
		Silver	7.0 g/t	
SOUTHEAST		Copper	0.402 %	Sample 2691914 from the south-southeast zone.
2014	Assay/analysis Rock	Silver	4.9 g/t	Assessment Report 34942.
VEIN		Gold	0.19 g/t	Rock sample (2691915) from the main zone.
2014	Assay/analysis Rock			Assessment Report 34942.
NORTHEAST		Copper	0.39 %	Two chip samples from the northeast zone yielded
2006	Assay/analysis Chip	Lead	0.25 %	from 0.36 to 0.39 per cent copper, 0.23 to 0.25 per cent
		Silver	6.8 g/t	lead, and 6.2 to 6.8 grams per tonne silver over 1.0
				metres each, respectively.
				Assessment Report 28649.
SOUTHEAST		Copper	2.56 %	A chip sample (G06350) from the south-southeast zone
2006	Assay/analysis Chip	Silver	17.6 g/t	over 1.0 metre.
				Assessment Report 28649.
TRENCH		Gold	30 g/t	Two chip samples (DK-GO6520 and DK-GO6518)
2006	Assay/analysis Chip			from trenches dug across the August 30 veins yielded
				values of 30 and 4.49 grams per tonne gold over 0.3 and
				1.0 metre, respectively, from the eastern trench.
				Assessment Report 28649.
VEIN		Gold	13.58 g/t	Over 2.4 metres.
2004	Assay/analysis Channel			Assessment Report 27636.
VEIN		Copper	0.15 %	Rock sample (185693) of vein material.
2004	Assay/analysis Rock	Tungsten	0.066 %	Assessment Report 27636.
		Silver	636 g/t	
		Gold	8.80 g/t	
		Lead	1 %	
		Zinc	1 %	
VEIN		Gold	25.48 g/t	Three grab samples were obtained from the poorly
2003	Assay/analysis Grab	Silver	29.3 g/t	exposed vein over a distance of 6 metres with one of the
				samples yielding 25.48 grams per tonne gold and 29.3
				grams per tonne silver from a grab of quartz-carbonate
				vein material.
				Assessment Report 27429, Figure 65.

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
FLOAT 1986 N	Assay/analysis Grab	Gold Silver	0.84 g/t 530.0 g/t	A float sample (MR-12) of malachite-stained tuff, taken from the ridge to the southwest. Assessment Report 15184.