

MINFILE Number: 094E 244	Name: AUGUST	Status: Showing
---------------------------------	---------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
NORTHEAST		Copper	0.611 %	Sample 2691918 from the northeast zone.
2014	N	Lead	0.423 %	Assessment Report 34942.
	Assay/analysis	Zinc	0.264 %	
	Rock	Silver	7.0 g/t	
SOUTHEAST		Copper	0.402 %	Sample 2691914 from the south-southeast zone.
2014	N	Silver	4.9 g/t	Assessment Report 34942.
	Assay/analysis			
	Rock			
VEIN		Gold	0.19 g/t	Rock sample (2691915) from the main zone.
2014	N			Assessment Report 34942.
	Assay/analysis			
	Rock			
NORTHEAST		Copper	0.39 %	Two chip samples from the northeast zone yielded
2006	N	Lead	0.25 %	from 0.36 to 0.39 per cent copper, 0.23 to 0.25 per cent
	Assay/analysis	Silver	6.8 g/t	lead, and 6.2 to 6.8 grams per tonne silver over 1.0
	Chip			metres each, respectively.
				Assessment Report 28649.
SOUTHEAST		Copper	2.56 %	A chip sample (G06350) from the south-southeast zone
2006	N	Silver	17.6 g/t	over 1.0 metre.
	Assay/analysis			Assessment Report 28649.
	Chip			
TRENCH		Gold	30 g/t	Two chip samples (DK-GO6520 and DK-GO6518)
2006	N			from trenches dug across the August 30 veins yielded
	Assay/analysis			values of 30 and 4.49 grams per tonne gold over 0.3 and
	Chip			1.0 metre, respectively, from the eastern trench.
				Assessment Report 28649.
VEIN		Gold	13.58 g/t	Over 2.4 metres.
2004	N			Assessment Report 27636.
	Assay/analysis			
	Channel			
VEIN		Copper	0.15 %	Rock sample (185693) of vein material.
2004	N	Tungsten	0.066 %	Assessment Report 27636.
	Assay/analysis	Silver	636 g/t	
	Rock	Gold	8.80 g/t	
		Lead	1 %	
		Zinc	1 %	
VEIN		Gold	25.48 g/t	Three grab samples were obtained from the poorly
2003	N	Silver	29.3 g/t	exposed vein over a distance of 6 metres with one of the
	Assay/analysis			samples yielding 25.48 grams per tonne gold and 29.3
	Grab			grams per tonne silver from a grab of quartz-carbonate
				vein material.
				Assessment Report 27429, Figure 65.

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
FLOAT 1986 N	Assay/analysis Grab	Gold Silver	0.84 g/t 530.0 g/t	A float sample (MR-12) of malachite-stained tuff, taken from the ridge to the southwest. Assessment Report 15184.