

<b>MINFILE Number:</b> 094E 247	<b>Name:</b> DRY POND	<b>Status:</b> Showing
---------------------------------	-----------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SKARN 2003	N Assay/analysis Chip	Copper Gold Silver	1.55 % 1.31 g/t 39.8 g/t	From a 1 metre chip sample. Assessment Report 27429.
SKARN 2003	N Assay/analysis Grab	Gold Silver	14.00 g/t 1069.6 g/t	Grab samples yielding values of up to 14.00 grams per tonne gold and 1069.6 grams per tonne silver from oxidized, iron-rich skarn material. Assessment Report 27429
SKARN 2003	N Assay/analysis Chip	Copper Lead Zinc Gold Silver	0.12 % 0.56 % 0.36 % 0.15 g/t 40.4 g/t	Over 2.0 metres. Assessment Report 27429
VEIN 2003	N Assay/analysis Rock	Copper Gold Silver	5.115 % 0.03 g/t 69.3 g/t	Samples from Dry Pond Canyon zone over 0.3 metre. Assessment Report 27429