

| | | |
|---------------------------------|---------------------------|-------------------------|
| MINFILE Number: 094E 302 | Name: BLACK GOSSAN | Status: Prospect |
|---------------------------------|---------------------------|-------------------------|

| Ore Zone/ Year/Report On | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
|-----------------------------|------------------------------|----------------|----------------------|---|
| DRILLHOLE 2017 N | Assay/analysis Drill Core | Gold | 0.12 g/t | And 0.017 per cent copper and 0.003 per cent molybdenum over 43.4 metres in drill hole BK17-04. Smith, A. (2019-04-04): Technical Report on the Baker Gold Project |
| SAMPLE 2012 N | Assay/analysis Rock | Gold Silver | 0.40 g/t 10.1 g/t | Twelve rocks samples from the Black Gossan area yielded values of up to. Assessment Report 34394 |
| DRILLHOLE 2004 N | Assay/analysis Drill Core | Gold Copper | 0.13 g/t 0.0192 % | Drilling intercepts, in 2004, on the Black Gossan area yielded broad anomalous copper-gold mineralization including 0.0095, 0.0037 and 0.0192 per cent copper with 0.08, 0.09 and 0.13 gram per tonne gold over 291.77, 185.06 and 166.76 metres in holes 04-26, -27 and -28, respectively. Assessment Report 27653 |
| DRILLHOLE 2002 N | Assay/analysis Drill Core | Gold Silver | 0.14 g/t 2.2 g/t | From a 1.83-metre drill interval. Assessment Report 27127. |
| DRILLHOLE 1997 N | Assay/analysis Drill Core | Gold | 0.59 g/t | Drilling on the North Black Gossan zone yielded 0.59 gram per tonne gold over 19.8 metres, including 1.54 grams per tonne gold over 6.42 metres in hole 97-9. Assessment Report 25619 |