

<b>MINFILE Number:</b>	094E 310	<b>Name:</b>	PIL SOUTH	<b>Status:</b>	Prospect
------------------------	----------	--------------	-----------	----------------	----------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
2024	N	Assay/analysis Drill Core	Copper	0.1 %	DDH PILS-24-006: 162 metre intercept, from 749 to 911 metres downhole; including 1.65 metres of 1.34 per cent copper 0.63 gram per tonne gold and 195 grams per tonne silver Press Release, Finlay Minerals Ltd., Nov. 12, 2024
			Gold	0.05 g/t	
			Silver	7 g/t	
			Zinc	0.18 %	
2024	N	Assay/analysis Grab	Copper	2.17 %	Rock sample F925665 from the 2023 sampling program; vuggy quartz ± pyrite-chalcopyrite-malachite ± magnetite ± galena vein Assessment Report 41688
			Silver	77.5 g/t	
2023	Y	Assay/analysis Grab	Copper	3.89 %	Rock sample F927323 (2022 sampling program); brecciated quartz-chalcopyrite vein Assessment Report 40755
			Silver	173 g/t	
2015	N	Assay/analysis Rock	Silver	45.9 g/t	Assessment Report 35995
2003	N	Assay/analysis Chip	Copper	0.38 %	Continuous chip sample collected over a 5-metre interval. <a href="http://www.finlayminerals.com/s/Home.asp">www.finlayminerals.com/s/Home.asp</a> .
2003	N	Assay/analysis Drill Core	Silver	200 g/t	Drillhole Pil S03-04 was drilled at an azimuth of 215 degrees and a dip of -60 degrees to 77.75 metres depth. This hole targeted the same geophysical-geochemical anomaly as DDH Pil S03-01. Pil S03-04 intersected an initial 23.5 metres of Takla Group augite porphyry basalt with the remainder being ash tuff. The latter was moderately to strongly silica magnetite flooded. A 1.5-metre fault zone within an intensely bleached and clay-altered interval (70.4 to 77.75 metres) contains greater than 200 parts per million silver. Assessment Report 27310
2002	N	Assay/analysis Rock	Silver	8.6 g/t	A rock sample (RM02PS27) from a 30-centimetre wide quartz vein hosting pyrite, chalcocite and chalcopyrite, taken along trend from the Lorne zone. Assessment Report 27055
			Copper	0.664 %	
			Zinc	0.343 %	
			Molybdenum	0.011 %	

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
L			Copper	1.73 %	A grab sample (PS-L18S-4+00E) of fractured basalt with quartz veining, hematite, pyrite, and chalcopyrite assayed greater than 1.00 per cent copper, 53.4 grams per tonne silver, 0.047 per cent molybdenum and 0.117 per cent zinc, while a chip sample (PRPS-04) taken across a 21-centimetre wide zone of chloritized andesite with stringers of quartz and chalcopyrite assayed 1.73 per cent copper, 46.1 grams per tonne silver and 0.101 per cent zinc. Both samples came from the Lorne zone. Assessment Report 26740
2001	N	Assay/analysis	Silver	46.1 g/t	
		Chip	Zinc	0.101 %	
L			Copper	0.210 %	Chip sampling of the Lorne zone over 20 metres and values of up to 0.378 per cent copper, 0.383 per cent zinc and 13.2 grams per tonne silver over 5 metres. Assessment Report 26383
2000	N	Assay/analysis	Zinc	0.214 %	
		Chip	Silver	6.3 g/t	
L			Copper	0.928 %	A 1-metre continuous chip sample (P99-054A) of quartz-chlorite altered rock hosting chalcopyrite, referred to as the Lorne zone and located approximately 600 metres to the south- south west at an elevation of approximately 1720 metres. Assessment Report 26104
1999	N	Assay/analysis	Silver	39.4 g/t	
		Chip	Gold	0.057 g/t	
NORTHWEST			Silver	2.2 g/t	Rock sample (JBP84) of chloritized gabbro with disseminated magnetite and pyrite taken near the south side of Jock Creek, approximately 1.1 kilometres to the northwest. Assessment Report 25282
1997	N	Assay/analysis	Copper	0.230 %	
		Rock			
SAMPLE			Gold	0.178 g/t	A rock sample (JBP101) of epidotized and chloritized pyroxene andesite hosting pyrite. Assessment Report 25282
1997	N	Assay/analysis	Silver	15.1 g/t	
		Rock	Lead	0.174 %	
SAMPLE			Gold	0.197 g/t	An outcrop rock sample (LPJ-2) of silicified andesite with disseminated pyrite. Assessment Report 25054
1996	N	Assay/analysis	Silver	41.4 g/t	
		Rock	Molybdenum	0.038 %	
			Copper	0.179 %	
SAMPLE			Gold	0.127 g/t	Rock sample (P12-7R) of argillized andesite, while a float sample (P12-6F) of silicified andesite with disseminated pyrite assayed 0.240 gram per tonne gold, 38.6 grams per tonne silver, 0.018 per cent molybdenum and 0.413 per cent copper. Assessment Report 24356
1995	N	Assay/analysis	Silver	23.3 g/t	
		Rock	Lead	0.206 %	
DRILLHOLE			Copper	0.177 %	Drill hole (P-1) was reported to have yielded 0.177 per cent copper over 4.6 metres of andesite hosting disseminated pyrite. Assessment Report 25811; Property File - Diamond Drill Record and Assay Log - Hole No. P-1 - Pillar
1969	N	Assay/analysis			
		Drill Core			