

MINFILE Number:		094E 436 Name: ASAP		AP	Status: Showing
Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE			Gold	0.052 g/t	three rock samples (Y445276 to Y445278) yielded from
		Assay/analysis	Silver	13.9 g/t	0.025 to 0.052 gram per tonne gold and 6.4 to 13.9
2018	Ν	Rock			grams per tonne silver
					Assessment Report 38447
SAMPLE			Gold	0.174 g/t	A rock sample H-53.
		Assay/analysis	Silver	9.4 g/t	Assessment Report 14700
1005	N	Rock		-	
1985	Ν	Rock			
SAMPLE			Gold	1.08 g/t	A rock sample (309), taken a short distance to the north
511011 22		A	Silver	80.0 g/t	of the 1982 samples.
		Assay/analysis Rock		C	Assessment Report 12911
1984	Ν	KOCK			1 -
SAMPLE			Gold	1.45 g/t	A rock sample (2-C-3055) assayed 1.45 grams per
STIMI EE			Silver	117 g/t	tonne gold and 117 grams per tonne silver, while
		Assay/analysis		. 0	another sample (2-E-0029) taken a short distance south
1982	Ν	Rock			yielded 0.50 gram per tonne gold and 32 grams per
					tonne silver.
					Assessment Report 11216
					rissessment report 11210