

<b>MINFILE Number:</b>	094F 012	<b>Name:</b>	GRAYLING	<b>Status:</b>	Showing
------------------------	----------	--------------	----------	----------------	---------

<b>Ore Zone/ Year/Report On</b>		<b>Tonnage/ Category</b>	<b>Commodity</b>	<b>Grade</b>	<b>Reference/ Comments</b>
SAMPLE			Copper	0.46 %	Across 1.0 metre.
1990	N	Assay/analysis Channel			Assessment Report 21437.
SAMPLE			Silver	27.8000 g/t	Grab samples (100, 101, 104 and 106) of semi-massive sulphide material. Traces of platinum (0.06 grams per ton) were also noted in the samples. Assessment Report 19124.
		Assay/analysis	Cobalt	0.5600 %	
1989	N	Grab	Copper	1.7000 %	
			Nickel	0.5000 %	
SAMPLE			Copper	0.152 %	A grab sample (8757) of quartzite with 15 per cent massive to disseminated and fracture filling sulphides (pyrite and chalcopyrite). Assessment Report 12594.
1984	N	Assay/analysis Grab			