

| | | |
|---------------------------------|-------------------|-----------------------------------|
| MINFILE Number: 094F 031 | Name: AKIE | Status: Developed Prospect |
|---------------------------------|-------------------|-----------------------------------|

| Ore Zone/ Year/Report On | Tonnage/ Category | Commodity | Grade | Reference/ Comments | |
|-----------------------------|----------------------|-----------|--------|------------------------|--|
| TOTAL | 22,700 | kt | Zinc | 8.32 % | Using a 5 per cent zinc cut-off grade. Makarenko, M. (2018-08-01): NI 43-101 Technical Report - Akie Project. |
| | Indicated | | Lead | 1.61 % | |
| 2018 | | | Silver | 14.1 g/t | |
| Y | | | | | |
| TOTAL | 7,500 | kt | Zinc | 7.04 % | Using a 5 per cent zinc cut-off grade. Makarenko, M. (2018-08-01): NI 43-101 Technical Report - Akie Project. |
| | Inferred | | Lead | 1.24 % | |
| 2018 | | | Silver | 12.0 g/t | |
| Y | | | | | |
| TOTAL | 8,100 | kt | Zinc | 6.8 % | Using a 5 per cent zinc cut-off grade. Information Circular 2018-1, page 30. |
| | Inferred | | Lead | 1.2 % | |
| 2016 | | | Silver | 11.2 g/t | |
| Y | | | | | |
| TOTAL | 19,600 | kt | Zinc | 8.17 % | Using a 5 per cent zinc cut-off grade. Information Circular 2018-1, page 30. |
| | Indicated | | Lead | 1.58 % | |
| 2016 | | | Silver | 13.6 g/t | |
| Y | | | | | |