

| | | |
|---------------------------------|-------------------|------------------------|
| MINFILE Number: 094K 076 | Name: JOHN | Status: Showing |
|---------------------------------|-------------------|------------------------|

| Ore Zone/ Year/Report On | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
|-----------------------------|-----------------------------|------------------|---------------------|---|
| SAMPLE 2020 | N Assay/analysis Rock | Copper | 0.194 % | A rock sample (Y646006) of silicified dolostone with malachite staining from the occurrence area. Assessment Report 38880. |
| SAMPLE 2005 | N Assay/analysis Chip | Copper Silver | 12.75 % 50.8 g/t | Chip samples (B374321) from the John area yielded values up to 12.75 per cent copper and 50.8 grams per tonne silver over 1.15 metres. Harrington, E. (2015-10-23): Technical Report on the Toro Property. |