MINFILE Number: 094M 002 **Name:** GEM **Status:** Prospect

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
TOTAL 1981 N	2,400 kt Unclassified	Fluorite	30 %	Possible geological reserves of approximately 2.4 million tonnes of fluorspar mineralization averaging 30 per cent fluorite. McCallum, N.G. (2012-12-12): Technical Report on the Liard Fluorspar Project.
TOTAL 1975 N	3,200 kt Unclassified	Fluorite	32 %	An engineering report estimated a possible reserve of 3.2 million tonnes grading 32 per cent CaF2. McCallum, N.G. (2012-12-12): Technical Report on the Liard Fluorspar Project.
DRILLHOLE 1972 N	Assay/analysis Drill Core	Fluorite	39.0000 %	Best intersection, over 15 metres, hole 72-12 in Gem E showing. Assessment Report 3975, page 10.