

<b>MINFILE Number:</b>	094M 002	<b>Name:</b>	GEM	<b>Status:</b>	Prospect
------------------------	----------	--------------	-----	----------------	----------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
TOTAL	2,400 kt Unclassified	Fluorite	30 %	Possible geological reserves of approximately 2.4 million tonnes of fluorspar mineralization averaging 30 per cent fluorite.
1981 N				McCallum, N.G. (2012-12-12): Technical Report on the Liard Fluorspar Project.
TOTAL	3,200 kt Unclassified	Fluorite	32 %	An engineering report estimated a possible reserve of 3.2 million tonnes grading 32 per cent CaF <sub>2</sub> .
1975 N				McCallum, N.G. (2012-12-12): Technical Report on the Liard Fluorspar Project.
DRILLHOLE		Fluorite	39.0000 %	Best intersection, over 15 metres, hole 72-12 in Gem E showing.
1972 N	Assay/analysis Drill Core			Assessment Report 3975, page 10.