

|                        |          |              |      |                |         |
|------------------------|----------|--------------|------|----------------|---------|
| <b>MINFILE Number:</b> | 094M 006 | <b>Name:</b> | FIRE | <b>Status:</b> | Showing |
|------------------------|----------|--------------|------|----------------|---------|

| Ore Zone/<br>Year/Report On |   | Tonnage/<br>Category          | Commodity | Grade     | Reference/<br>Comments                                                                 |
|-----------------------------|---|-------------------------------|-----------|-----------|----------------------------------------------------------------------------------------|
| SAMPLE                      |   |                               | Fluorite  | 44.4 %    | Three samples (380012 to 380014) yielded from 37.6 to 44.4 per cent CaF <sub>2</sub> . |
| 2012                        | N | Assay/analysis<br>Channel     |           |           | McCallum, N.G. (2012-12-12): Technical Report on the Liard Fluorspar Project.          |
| DRILLHOLE                   |   |                               | Fluorite  | 37.0000 % | Hole 72-37, over 20 metres.                                                            |
| 1972                        | N | Assay/analysis<br>Drill Core  |           |           | Assessment Report 3975.                                                                |
| SAMPLE                      |   |                               | Fluorite  | 42.9400 % | "Head assay" of bulk sample number 5, of limestone breccia.                            |
| 1972                        | N | Assay/analysis<br>Bulk Sample |           |           | Assessment Report 3840.                                                                |