

<b>MINFILE Number:</b> 103C 002	<b>Name:</b> HAIDA GOLD	<b>Status:</b> Prospect
---------------------------------	-------------------------	-------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
LOWER 1987	N Assay/analysis Grab	Gold	11.5 g/t	sampling of lower adit Property File - R.A. Lake [1987-09-16]: Geological Survey of the Kootenay Claims
UPPER 1987	N Assay/analysis Grab	Gold	24.3 g/t	sampling of upper adit Property File - R.A. Lake [1987-09-16]: Geological Survey of the Kootenay Claims
DRILLHOLE 1985	N Assay/analysis Drill Core	Gold	2.0200 g/t	Drill hole sample assayed over a length of 0.9 metre. Assessment Report 13649.
LOWER 1979	N Assay/analysis Chip	Gold	3.6 g/t	Sampling of the lower adit, approximately 6 metres from the adit portal, yielded 3.6 grams per tonne gold over 0.6 metre Property File - Chevron Standard Limited [1979-06-13]: Correspondence and notes - Blue Mule property (Blue claims) - Queen Charlotte gold - M-466
VEIN 1979	N Assay/analysis Chip	Gold	24.3 g/t	a chip sample from a vein located 150 metres east of the upper adit portal assayed 24.3 grams per tonne gold over 45 centimetres Property File - Noranda Exploration Co. Ltd. [1979-07-30]: Assays - Kootenay Inlet Property
UPPER 1979	N Assay/analysis Chip	Gold	53.4 g/t	a chip sample (5437) from the upper adit assayed 53.4 grams per tonne gold over 23 centimetres Property File - Noranda Exploration Co. Ltd. [1979-07-30]: Assays - Kootenay Inlet Property
DRIFT 1934	N Assay/analysis Chip	Gold	7.3 g/t	detailed sampling in the 85-metre long drift adit (A-1 adit) showed values varying from 0.69 to 48.7 grams per tonne gold, with an average assay value of 7.3 grams per tonne gold across a width of 0.73 metre along the length of the tunnel Annual Report 1934; B3,B4
TUNNEL 1933	N Assay/analysis Chip	Gold	17.1 g/t	two sets of samples from the no.1 tunnel (C vein) assayed 4.4 and 17.1 grams per tonne gold over 54 centimetres for the first 13.5 metres of the tunnel, respectively, while the average of surface sampling above the tunnel yielded 10.1 grams per tonne gold across 72.5 centimetres Property File - C.C. Starr [1933-10-15]: Report of Examination of the Haida Gold Mines Ltd. Property

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
VEIN			Gold	25.0 g/t	sampling of the F vein yielded up to 25.0 grams per tonne gold over 16 centimetres
1933	N	Assay/analysis Rock			Property File - C.C. Starr [1933-10-15]: Report of Examination of the Haida Gold Mines Ltd. Property
OPENCUT			Gold	21.9 g/t	a sample from a 0.3 to 0.4 metre wide quartz vein with minor chalcopyrite exposed in the face of an open-cut
1932	N	Assay/analysis Grab	Silver	10.3 g/t	Property File - J.T. Mandy [1932-12-03]: Annual Report - Kootenay Group