

MINFILE Number:	103C 002	Name:	HAIDA GOLD	Status:	Prospect
------------------------	----------	--------------	------------	----------------	----------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
LOWER			Gold	11.5 g/t	sampling of lower adit
1987	N	Assay/analysis Grab			Property File - R.A. Lake [1987-09-16]: Geological Survey of the Kootenay Claims
UPPER			Gold	24.3 g/t	sampling of upper adit
1987	N	Assay/analysis Grab			Property File - R.A. Lake [1987-09-16]: Geological Survey of the Kootenay Claims
DRILLHOLE			Gold	2.0200 g/t	Drill hole sample assayed over a length of 0.9 metre.
1985	N	Assay/analysis Drill Core			Assessment Report 13649.
LOWER			Gold	3.6 g/t	Sampling of the lower adit, approximately 6 metres from the adit portal, yielded 3.6 grams per tonne gold over 0.6 metre
1979	N	Assay/analysis Chip			Property File - Chevron Standard Limited [1979-06-13]: Correspondence and notes - Blue Mule property (Blue claims) - Queen Charlotte gold - M-466
VEIN			Gold	24.3 g/t	a chip sample from a vein located 150 metres east of the upper adit portal assayed 24.3 grams per tonne gold over 45 centimetres
1979	N	Assay/analysis Chip			Property File - Noranda Exploration Co. Ltd. [1979-07-30]: Assays - Kootenay Inlet Property
UPPER			Gold	53.4 g/t	a chip sample (5437) from the upper adit assayed 53.4 grams per tonne gold over 23 centimetres
1979	N	Assay/analysis Chip			Property File - Noranda Exploration Co. Ltd. [1979-07-30]: Assays - Kootenay Inlet Property
DRIFT			Gold	7.3 g/t	detailed sampling in the 85-metre long drift adit (A-1 adit) showed values varying from 0.69 to 48.7 grams per tonne gold, with an average assay value of 7.3 grams per tonne gold across a width of 0.73 metre along the length of the tunnel
1934	N	Assay/analysis Chip			Annual Report 1934; B3,B4
TUNNEL			Gold	17.1 g/t	two sets of samples from the no.1 tunnel (C vein) assayed 4.4 and 17.1 grams per tonne gold over 54 centimetres for the first 13.5 metres of the tunnel, respectively, while the average of surface sampling above the tunnel yielded 10.1 grams per tonne gold across 72.5 centimetres
1933	N	Assay/analysis Chip			Property File - C.C. Starr [1933-10-15]: Report of Examination of the Haida Gold Mines Ltd. Property

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
VEIN			Gold	25.0 g/t	sampling of the F vein yielded up to 25.0 grams per tonne gold over 16 centimetres
1933	N	Assay/analysis Rock			Property File - C.C. Starr [1933-10-15]: Report of Examination of the Haida Gold Mines Ltd. Property
OPENCUT			Gold	21.9 g/t	a sample from a 0.3 to 0.4 metre wide quartz vein with
		Assay/analysis	Silver	10.3 g/t	minor chalcopyrite exposed in the face of a open-cut
1932	N	Grab			Property File - J.T. Mandy [1932-12-03]: Annual Report - Kootenay Group