**MINFILE Number:** 103I 020 **Name:** MARTIN **Status:** Showing

| Ore Zone/ Year/Report On | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
|---|---|---|---|---|
| SAMPLE<br>2003 N | Assay/analysis<br>Grab | Gold<br>Silver | 34.0 g/t<br>260.9 g/t | Two grab samples (CDK03R84 and TTKL03R088) are reported to have assayed 25.0 and 34.0 grams per tonne gold with 260.9 and 83.0 grams per tonne silver. Daignault, P.M., Sharp, R.J. (2007-12-27): 2007 Exploration and Geological Report for the Kalum Property; Hutter, J.M. (2012-02-22): Technical Report for the Kalum Property |
| SAMPLE<br>1928 N | Assay/analysis<br>Chip | Silver<br>Gold<br>Lead | 137.0000 g/t<br>8.2000 g/t<br>4.0000 % | The sample width is 30.0 centimetres. Minister of Mines Annual Report 1928. |