

|                        |          |              |             |                |               |
|------------------------|----------|--------------|-------------|----------------|---------------|
| <b>MINFILE Number:</b> | 103I 022 | <b>Name:</b> | HOPE SILVER | <b>Status:</b> | Past Producer |
|------------------------|----------|--------------|-------------|----------------|---------------|

| Ore Zone/<br>Year/Report On |   | Tonnage/<br>Category   | Commodity | Grade        | Reference/<br>Comments  |
|-----------------------------|---|------------------------|-----------|--------------|---|
| 2007                        | N | Assay/analysis<br>Chip | Gold      | 0.034 g/t    | A 5.5 metre continuous chip sample was taken in 2007 by Strategic Metals where the zone is exposed in a creek bed that flows through an old glory hole. The showing consists of pyrite, sphalerite, galena, chalcopryite and tetrahedrite in a siliceous and carbonate rich breccia matrix.<br>ARIS 30468 |
|                             |   |                        | Silver    | 431 g/t      |   |
|                             |   |                        | Copper    | 1.71 %       |   |
|                             |   |                        | Lead      | 2.57 %       |   |
|                             |   |                        | Zinc      | 7.30 %       |   |
| 1969                        | N | Assay/analysis<br>Chip | Silver    | 432.0000 g/t | The sample width is 4.5 metres.<br>Geology, Exploration and Mining in British Columbia, 1969.   |
|                             |   |                        | Copper    | 0.7600 %     |   |
|                             |   |                        | Lead      | 1.9000 %     |   |
|                             |   |                        | Zinc      | 6.7000 %     |   |