

<b>MINFILE Number:</b> 103I 154	<b>Name:</b> PADDY MAC	<b>Status:</b> Showing
---------------------------------	------------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
VEIN		Gold	60.3 g/t	sample KR103
	Assay/analysis	Silver	144 g/t	Assessment Report 23766
1994	N Grab	Copper	0.632 %	
		Lead	1 %	
VEIN		Gold	16.67 g/t	sample 467854
	Assay/analysis			Assessment Report 20504
1990	N Rock			
VEIN		Gold	3.06 g/t	sample 467853
	Assay/analysis			Assessment Report 20504
1990	N Chip			
SAMPLE		Silver	253.7000 g/t	The sample width was 30.0 centimetres.
	Assay/analysis	Gold	373.7000 g/t	Assessment Report 15337.
1986	N Chip	Copper	0.0600 %	
		Lead	0.3800 %	
		Zinc	0.0200 %	
VEIN		Silver	176.2200 g/t	Average of 21 chip samples taken across an average
	Assay/analysis	Gold	19.5400 g/t	width of 0.36 metre.
1980	N Chip			Property File - Holt, 1987.