

|                                 |                   |                        |
|---------------------------------|-------------------|------------------------|
| <b>MINFILE Number:</b> 103I 168 | <b>Name:</b> POES | <b>Status:</b> Showing |
|---------------------------------|-------------------|------------------------|

| Ore Zone/<br>Year/Report On | Tonnage/<br>Category | Commodity | Grade        | Reference/<br>Comments  |
|-----------------------------|----------------------|-----------|--------------|---|
| SAMPLE                      |                      | Silver    | 209.0000 g/t | The sample width is 38.0 centimetres.<br>Minister of Mines Annual Report 1940, page 55. |
|                             | Assay/analysis       | Gold      | 0.7000 g/t   |   |
| 1940                        | N                    | Copper    | 4.5000 %     |   |
|                             | Chip                 | Lead      | 6.8000 %     |   |
|                             |                      | Zinc      | 8.6000 %     |   |