

MINFILE Number:		Name:		Status:	
Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments	
VEIN 2005	N Assay/analysis Grab	Gold Silver	45.1 g/t 50.1 g/t	grab samples (CGKMF020 and 021) from 75 and 40 centimetre wide veins yielded 26.6 and 45.1 grams per tonne gold with 23.8 and 50.1 grams per tonne silver, respectively	Daignault, P.M., Sharp, R.J. (2007-12-27): 2007 Exploration and Geological Report for the Kalum Property
DRILLHOLE 2004	N Assay/analysis Drill Core	Gold	16.3 g/t	Over 0.3 metre.	Exploration and Mining in British Columbia 2004, page 33
1 1981	N Assay/analysis Chip	Silver Gold Lead	80.5700 g/t 11.2500 g/t 1.4000 %	Average chip sample over 300 metre length. Assessment Report 10523.	
2 1981	N Assay/analysis Chip	Gold Silver Lead	2.09 g/t 8.23 g/t 0.1 %		Assessment Report 10523
TRENCH 1959	N Assay/analysis Rock	Gold Silver	17.2 g/t 95.8 g/t	Average grade of samples from trench, while individual samples yielded up to 169.6 grams per tonne gold and 5917 grams per tonne silver. Daignault, P.M., Sharp, R.J. (2007-12-27): 2007 Exploration and Geological Report for the Kalum Property	Daignault, P.M., Sharp, R.J. (2007-12-27): 2007 Exploration and Geological Report for the Kalum Property