

<b>MINFILE Number:</b>	103I 174	<b>Name:</b>	CHRIS	<b>Status:</b>	Prospect
------------------------	----------	--------------	-------	----------------	----------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
2005	N	Assay/analysis Grab	Gold	45.1 g/t	grab samples (CGKMOV020 and 021) from 75 and 40 centimetre wide veins yielded 26.6 and 45.1 grams per tonne gold with 23.8 and 50.1 grams per tonne silver, respectively Daignault, P.M., Sharp, R.J. (2007-12-27): 2007 Exploration and Geological Report for the Kalum Property
			Silver	50.1 g/t	
2004	N	Assay/analysis Drill Core	Gold	16.3 g/t	Over 0.3 metre. Exploration and Mining in British Columbia 2004, page 33
1981	N	Assay/analysis Chip	Silver	80.5700 g/t	Average chip sample over 300 metre length. Assessment Report 10523.
			Gold	11.2500 g/t	
			Lead	1.4000 %	
1981	N	Assay/analysis Chip	Gold	2.09 g/t	Assessment Report 10523
			Silver	8.23 g/t	
			Lead	0.1 %	
1959	N	Assay/analysis Rock	Gold	17.2 g/t	Average grade of samples from trench, while individual samples yielded up to 169.6 grams per tonne gold and 5917 grams per tonne silver. Daignault, P.M., Sharp, R.J. (2007-12-27): 2007 Exploration and Geological Report for the Kalum Property
			Silver	95.8 g/t	