

| | | |
|---------------------------------|--------------------|-------------------------|
| MINFILE Number: 103I 174 | Name: CHRIS | Status: Prospect |
|---------------------------------|--------------------|-------------------------|

| Ore Zone/ Year/Report On | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
|-----------------------------|------------------------------|-----------|-------------|---|
| VEIN | | Gold | 45.1 g/t | grab samples (CGKMOV20 and 021) from 75 and 40 centimetre wide veins yielded 26.6 and 45.1 grams per tonne gold with 23.8 and 50.1 grams per tonne silver, respectively Daignault, P.M., Sharp, R.J. (2007-12-27): 2007 Exploration and Geological Report for the Kalum Property |
| 2005 | Assay/analysis Grab | Silver | 50.1 g/t | |
| DRILLHOLE | | Gold | 16.3 g/t | Over 0.3 metre. Exploration and Mining in British Columbia 2004, page 33 |
| 2004 | Assay/analysis Drill Core | | | |
| 1 | | Silver | 80.5700 g/t | Average chip sample over 300 metre length. Assessment Report 10523. |
| | Assay/analysis | Gold | 11.2500 g/t | |
| 1981 | Chip | Lead | 1.4000 % | |
| 2 | | Gold | 2.09 g/t | Assessment Report 10523 |
| | Assay/analysis | Silver | 8.23 g/t | |
| 1981 | Chip | Lead | 0.1 % | |
| TRENCH | | Gold | 17.2 g/t | Average grade of samples from trench, while individual samples yielded up to 169.6 grams per tonne gold and 5917 grams per tonne silver. Daignault, P.M., Sharp, R.J. (2007-12-27): 2007 Exploration and Geological Report for the Kalum Property |
| 1959 | Assay/analysis Rock | Silver | 95.8 g/t | |