

<b>MINFILE Number:</b> 103I 188	<b>Name:</b> BRENTFORD	<b>Status:</b> Showing
---------------------------------	------------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
VEIN		Silver	1644 g/t	Sample 3: Quartz vein; approx 1m thick; vein inundated with wallrock stylonite material; on edges of vein selvage appears to be galena and sphalerite as massive blebs and smears with an abundance of pyrite and chalcopyrite ARIS 36204
	Assay/analysis	Gold	0.31 g/t	
2016	Grab	Copper	2.33 %	
		Lead	50.2 %	
		Zinc	3.69 %	
VEIN		Gold	240 g/t	Sample (B 38 R) Assessment Report 31459
	Assay/analysis	Silver	145.2 g/t	
2010	Rock	Copper	0.598 %	
		Zinc	0.207 %	
		Lead	1 %	
1		Gold	18.54 g/t	two samples (S615 and S616) from the J1 vein Assessment Report 27225
	Assay/analysis	Silver	541 g/t	
2003	Rock	Lead	1.43 %	
2		Silver	415 g/t	A sample (S613) of the J2 vein Assessment Report 27225
	Assay/analysis	Gold	29.54 g/t	
2003	Rock	Copper	0.185 %	
		Lead	4.17 %	
		Zinc	0.121 %	
DUMP		Silver	377.0000 g/t	The sample was selected from a dump. Minister of Mines, Annual Report 1932, pages 84,85.
	Assay/analysis	Gold	1.4000 g/t	
1932	Grab	Copper	1.0000 %	
		Lead	11.0000 %	
		Zinc	8.0000 %	