

<b>MINFILE Number:</b> 103P 088	<b>Name:</b> SILVERADO	<b>Status:</b> Past Producer
---------------------------------	------------------------	------------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE 2011	N Assay/analysis Grab	Silver Gold Lead Zinc	409.0 g/t 0.723 g/t 4.00 % 2.33 %	A grab sample (SM-26) from the Silverado occurrence area. Assessment Report 32668
SAMPLE 1987	N Assay/analysis Rock	Copper Lead Zinc Silver Gold	0.94 % 15.92 % 2.16 % 1179.8 g/t 0.72 g/t	Six select samples (2152, 2154, 2155, 2158, 2161, 2179) from the same area are reported to have yielded from 0.22 per cent copper, 0.56 per cent lead, 0.18 per cent zinc, 180.1 grams per tonne silver and 0.25 gram per tonne gold to 0.94 per cent copper, 15.92 per cent lead, 2.16 per cent zinc, 1179.8 grams per tonne silver and 0.72 gram per tonne gold. Assessment Report 15574
EAST 1985	N Assay/analysis Rock	Gold Silver	1.31 g/t 2177 g/t	An undescribed sample (9419) taken several hundred metres east of the plotted location of the Silverado occurrence. Assessment Report 14341
SHEAR 1946	N Assay/analysis Chip	Silver Gold Cadmium Copper Lead Zinc	2866.0000 g/t 0.6900 g/t 0.0900 % 0.2000 % 8.9000 % 6.3000 %	A 0.381-metre chip sample across Number 1 shear zone. Minister of Mines Annual Report 1946, page 78.