

<b>MINFILE Number:</b>	103P 088	<b>Name:</b>	SILVERADO	<b>Status:</b>	Past Producer
------------------------	----------	--------------	-----------	----------------	---------------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE  2011	N	Assay/analysis Grab	Silver	409.0 g/t	A grab sample (SM-26) from the Silverado occurrence area. Assessment Report 32668
			Gold	0.723 g/t	
			Lead	4.00 %	
			Zinc	2.33 %	
SAMPLE  1987	N	Assay/analysis Rock	Copper	0.94 %	Six select samples (2152, 2154, 2155, 2158, 2161, 2179) from the same area are reported to have yielded from 0.22 per cent copper, 0.56 per cent lead, 0.18 per cent zinc, 180.1 grams per tonne silver and 0.25 gram per tonne gold to 0.94 per cent copper, 15.92 per cent lead, 2.16 per cent zinc, 1179.8 grams per tonne silver and 0.72 gram per tonne gold. Assessment Report 15574
			Lead	15.92 %	
			Zinc	2.16 %	
			Silver	1179.8 g/t	
EAST  1985	N	Assay/analysis Rock	Gold	1.31 g/t	An undescribed sample (9419) taken several hundred metres east of the plotted location of the Silverado occurrence. Assessment Report 14341
			Silver	2177 g/t	
SHEAR  1946	N	Assay/analysis Chip	Silver	2866.0000 g/t	A 0.381-metre chip sample across Number 1 shear zone. Minister of Mines Annual Report 1946, page 78.
			Gold	0.6900 g/t	
			Cadmium	0.0900 %	
			Copper	0.2000 %	
			Lead	8.9000 %	
			Zinc	6.3000 %	