MINFILE Number: 103P 136 **Name:** LOUISE **Status:** Showing

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE 1942 N	Assay/analysis Grab	Tungsten	0.2100 %	Equivalent to 0.27 per cent tungstic oxide (WO3). Highest assay from grab samples. Bulletin 10, page 54.