

MINFILE Number:		Name:		Status:	
Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments	
VEIN 2018	N	Gold Assay/analysis Chip	2.75 g/t Silver 19.71 g/t	Sample # X516953: 1m chip 037°/76° trending vein/fault; 50 centimetre wide shear containing a 30 centimetre wide quartz-carbonate vein with an estimated 8-10 per cent arsenopyrite and pyrite; vein margins are silicified and pyrite-altered for up to 1m outside vein. ARIS 38189	
VEIN 2018	N	Gold Assay/analysis Grab	10.87 g/t Silver 30 g/t Copper 0.225 % Zinc 0.28 %	Sample # X516954: grab of 10-15 centimetre quartz vein +/- Fe-carbonate. Containing galena, chalcopyrite, pyrite hosted in intermediate volcanic traced for approximately 15 metres. Vein trends 184°/59°. ARIS 38189	
SAMPLE 1994	N	Zinc Assay/analysis Grab	23.55 % Lead 4.93 % Silver 95.4 g/t Copper 0.27 %	Grab sample ERK-649. Assessment Report 23986.	