

<b>MINFILE Number:</b> 104A 164	<b>Name:</b> SLIPPERY IAN	<b>Status:</b> Prospect
---------------------------------	---------------------------	-------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE		Gold	0.62 g/t	Seventeen samples were collect from the Slippery Ian occurrence and yielded values of up to 0.62 gram per tonne gold, 116 grams per tonne silver, 0.66 per cent copper, 13.2 per cent lead and 16.8 per cent zinc. Bravewolf Consulting (2020-07-17): 2020 Technical (NI 43-101) Report on the Independence and Slippery Ian Properties
	Assay/analysis	Silver	116 g/t	
2017	N	Copper	0.66 %	
	Rock	Lead	13.2 %	
		Zinc	16.8 %	
TRENCH		Silver	57.9000 g/t	Average assay from 12 chip samples of the mineralized quartz vein; across 0.6 metre. Also 0.2 per cent cadmium. Assessment Report 21457.
	Assay/analysis	Gold	0.9000 g/t	
1990	N	Copper	0.5000 %	
	Chip	Lead	6.6000 %	
		Tungsten	0.3000 %	
		Zinc	8.5000 %	