

MINFILE Number: 104A 164	Name: SLIPPERY IAN	Status: Prospect
---------------------------------	---------------------------	-------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE 2017	Assay/analysis Rock	Gold Silver Copper Lead Zinc	0.62 g/t 116 g/t 0.66 % 13.2 % 16.8 %	Seventeen samples were collect from the Slippery Ian occurrence and yielded values of up to 0.62 gram per tonne gold, 116 grams per tonne silver, 0.66 per cent copper, 13.2 per cent lead and 16.8 per cent zinc. Bravewolf Consulting (2020-07-17): 2020 Technical (NI 43-101) Report on the Independence and Slippery Ian Properties
TRENCH 1990	Assay/analysis Chip	Silver Gold Copper Lead Tungsten Zinc	57.9000 g/t 0.9000 g/t 0.5000 % 6.6000 % 0.3000 % 8.5000 %	Average assay from 12 chip samples of the mineralized quartz vein; across 0.6 metre. Also 0.2 per cent cadmium. Assessment Report 21457.