MINFILE Number: 104B 253 **Name:** TIDE SOUTH **Status:** Showing

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
SOUTH 2005	N	Assay/analysis Rock	Gold Silver Copper	10.70 g/t 93 g/t 0.493 %	a sample (275705) assayed 10.70 grams per tonne gold, 93 grams per tonne silver and 0.493 per cent copper, while chip samples (275701, 275702 and 275704) yielded from 1.47 to 4.81 grams per tonne gold with 6.0 to 32.0 grams per tonne silver over 0.30 to 1.80 metres Heffernan, R.S. (2006-11-15): Summary Report on the Tide Project
SOUTH 2004	N	Assay/analysis Drill Core	Gold	1.91 g/t	0.81 metre Assessment Report 27590
SOUTH 2004	N	Assay/analysis Chip	Gold Silver	4.57 g/t 17.2 g/t	A surface chip sample (273942), performed in 2004, yielded up to 4.57 grams per tonne gold and 17.2 grams per tonne silver over 2.00 metres, while grab samples yielded up to 8.79 grams per tonne gold, 173 grams per tone silver, 1.90 per cent copper, 7.10 per cent lead, 8.55 per cent zinc and greater than 1.00 per cent antimony Heffernan, R.S. (2006-11-15): Summary Report on the Tide Project
SOUTH 2001	N	Assay/analysis Chip	Gold Silver Copper	19.93 g/t 48.4 g/t 0.195 %	a sample (276392) assayed 19.93 grams per tonne gold, 48.4 grams per tonne silver and 0.195 per cent copper over 0.50 metre, while other samples yielded up to 4.19 grams per tonne gold, 172 grams per tonne silver, 0.526 per cent copper, 9.51 per cent lead, 1.48 per cent zinc and greater than 1.00 per cent antimony Heffernan, R.S. (2006-11-15): Summary Report on the Tide Project
SOUTH 1983	N	Assay/analysis Grab	Silver Gold	192.6900 g/t 115.8900 g/t	Most samples assayed much lower but were still significant. Assessment Report 11528.