

<b>MINFILE Number:</b>	104B 401	<b>Name:</b>	52 ZONE	<b>Status:</b>	Prospect
------------------------	----------	--------------	---------	----------------	----------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
2005	N	Assay/analysis Drill Core	Silver	8.8 g/t	Drill intersection over 0.59 metres in hole TIDE05-06, while four step-out drill holes yielded up to 0.56 gram per tonne gold over 210.9 metres Serengeti Resources website (www.serengetiresources.com); Heffernan, R.S. (2006-11-15): Summary Report on the Tide Project
			Gold	6.24 g/t	
2005	N	Assay/analysis Rock	Gold	18.80 g/t	samples from the north west strike extension and the south west parallel vein trend yielded up to 5.59 and 18.80 grams per tonne gold with 602 and 2300 grams per tonne silver, respectively Heffernan, R.S. (2006-11-15): Summary Report on the Tide Project
			Silver	2300 g/t	
2005	N	Assay/analysis Chip	Gold	158.50 g/t	two chip samples (270274 and 270282) of vein and vein/host from the main 52 zone yielded 158.50 and 23.50 grams per tonne gold with 363 and 47.5 grams per tonne silver over 0.25 and 1.00 metre Heffernan, R.S. (2006-11-15): Summary Report on the Tide Project
			Silver	363 g/t	
2005	N	Assay/analysis Grab	Gold	460.00 g/t	a grab sample (345727) from a sub-parallel vein yielded 460.00 grams per tonne gold and 2930 grams per tonne silver Heffernan, R.S. (2006-11-15): Summary Report on the Tide Project
			Silver	2930 g/t	
2004	N	Assay/analysis Chip	Gold	593 g/t	two chip samples (279975 and 279968) from the main 52 zone yielded up to 593 and 360 grams per tonne gold with 14708 and 7920 grams per tonne silver over 0.50 metre each, respectively Heffernan, R.S. (2006-11-15): Summary Report on the Tide Project
			Silver	14708 g/t	
2004	N	Assay/analysis Grab	Gold	2.91 g/t	grab samples (273615 and 273913) from the north west strike extension and the south west parallel vein trend yielded 2.33 and 2.91 grams per tonne gold with 10.2 and 102 grams per tonne silver, respectively Heffernan, R.S. (2006-11-15): Summary Report on the Tide Project
			Silver	102 g/t	