

<b>MINFILE Number:</b>	104B 615	<b>Name:</b>	BGS	<b>Status:</b>	Showing
------------------------	----------	--------------	-----	----------------	---------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
B	2019	N	Assay/analysis Rock	Gold	Three rock samples from the BGS zone yielded an average of 3.68 grams per tonne gold (up to 4.04 grams per tonne) and 74.2 grams per tonne silver (up to 170.0 grams per tonne). Mitchell, A.J., Prowse, N.D. (2020-06-08): NI 43-101 Technical Report on the Doc Property
				Silver	
RIDGE	2019	N	Assay/analysis Chip	Gold	A 0.35-metre-chip sample from the Galena Ridge zone yielded 12.80 grams per tonne gold and 263.0 grams per tonne silver, while a channel sample from the same zone yielded 7.75 grams per tonne gold and 286.0 grams per tonne silver over 0.44 metre. Mitchell, A.J., Prowse, N.D. (2020-06-08): NI 43-101 Technical Report on the Doc Property
				Silver	
VEIN	2019	N	Assay/analysis Channel	Gold	Channel sampling of the Q19 zone over 0.70 metre. Mitchell, A.J., Prowse, N.D. (2020-06-08): NI 43-101 Technical Report on the Doc Property
				Silver	
				Copper	
				Lead	
B	2018	N	Assay/analysis Rock	Gold	A rock sample from a 2-centimetre-wide quartz vein hosting pyrite, chalcopyrite, magnetite and malachite, taken a short distance west of the BGS zone. Mitchell, A.J., Prowse, N.D. (2020-06-08): NI 43-101 Technical Report on the Doc Property
				Silver	
				Copper	
B	1999	N	Assay/analysis Grab	Gold	Assessment Report 26256.
				Silver	
VEIN	1987	N	Assay/analysis Chip	Gold	Trenching on the Q19 vein by Magna Ventures is reported to have yielded up to 64.40 grams per tonne gold and 765.1 grams per tonne silver over 1.10 metres with an average of 7.65 grams per tonne gold and 72.1 grams per tonne silver over 5.78 metres, while a 'high-grade' grab sample assayed up to 210.00 grams per tonne gold and 587.8 grams per tonne silver. Mitchell, A.J., Prowse, N.D. (2020-06-08): NI 43-101 Technical Report on the Doc Property
				Silver	